

| | | | |
|--------------------|--|-----|--|
| CI/SfB | | Yt3 | |
| CAW Z20 | | | |
| Uniclass L6739:P99 | | | |

Description

TN015 is a single-sided EPDM closed cell foam.

Packaging

Thickness: 2, 3, 4, 5, 6, 8, 10 and 12 mm

Width: 6 to 950 mm

Any width within the range noted above can be cut subject to minimum order quantities. Stock sizes are available and our Customer Service team can supply details as well as advise on cut to order sizes, minimum order quantities and lead time.

Technical Information

| Property | Results |
|--------------------------|---|
| Flammability | Self extinguishing, approved to FMVSS302 |
| Foam Type | EPDM closed cell |
| Foam Density | 130- 170 kg/m ³ |
| Adhesive Format | Single sided |
| Adhesive Type | Acrylic adhesive |
| Tape Colour | Black |
| Application Temperature | +10°C |
| Service Temperature | -30°C to +90°C |
| Recommended Compressions | 30% |
| Storage | Store in shaded dry conditions between +10°C and +20°C |
| Shelf Life | 24 months when stored as recommended in original unopened packaging |

Preparation

- Ensure bonding surfaces are free from irregularities and loose particles which may impair adhesion.
- Dust, dirt and grease can be removed using AT115 Solvent Cleaner. Where substrates are sensitive to solvent attack, clean with warm water and allow to dry.
- The substrate must always be dry before application of the tape.

Application

- The exposed adhesive face should be unwound gradually and carefully located onto surface of the substrate. Care must be taken to avoid compressing or stretching the tape during location- this could induce peeling forces and cause the tape to lift from the substrate.
- Once the tape has been positioned then apply even pressure throughout the length using a roller, starting at the centre and moving to each end to avoid stretching.
- With double sided tapes the protective release film is not removed until immediately prior to joint assembly.
- The assembly must provide sufficient force to compress the tape by 20% of original thickness for security applications and 30% if weatherseal performance is required. Over compression should be avoided.
- Joints may be made by mitring corners or butting the tape ends tightly together. In all cases the tapes should be cleanly cut at slightly longer length than required to ensure compression of the jointing faces and formation of a tight joint.



TN015

Synthetic Rubber Foam Tape

Usage / Purpose

TN015 can be used for a wide range of applications requiring a positive water seal and good chemical resistance. It can also be used for open and close seals.

Key Benefits

- CFC and HCFC free
- Good chemical resistance
- Self extinguishing

TN015

Synthetic Rubber Foam Tape



Please Note

The adhesive is not UV resistant and should not be exposed to the sun, as degradation of adhesive will occur.

Users are advised to conduct their own tests in order to determine the suitability of the product for the particular application. All slitting and length tolerances are to British Standards, but other tolerances are available by request.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco

illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



tremco illbruck Limited
Coupland Road
Hindley Green, Wigan WN2 4HT
United Kingdom
T: +44 1942 251400
F: +44 1942 251410

sales.uk@tremco-illbruck.com
www.tremco-illbruck.co.uk