

Cl/SfB		Yt3	
CAW Z20			
Uniclass L6739:P7112			

Description

PU010 is a rapid curing gun grade polyurethane, collapsing foam adhesive.

Colour

Green

Packaging

750 ml canisters (12 per carton)

Technical Information

Characteristic	Standard	Classification
Composition		Polyurethane Adhesive
Density	EN 17333-1	15 - 25 kg/m ³
Tack Free Time	EN 17333-3	10 minutes
Loading Time		3 hours
Tensile Strength on 8 mm wide joint	ETAG 004	106 kPa
Thermal Conductivity		36 mW/m.K
Application Temperature		Canister: +10°C to +30°C Ambient: +5°C to +35°C
Service Temperature		Short term: -40°C to +130°C Long term: -40°C to +90°C
Storage	Store in shaded, dry conditions between +10°C and +30°C Store canisters upright	
Shelf Life	24 months when stored as recommended in original, unopened containers	

Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Preparation

- Always carry out a test to confirm compatibility prior to use.
- Protect floor coverings with paper or a plastic film.
- The surfaces must be dry, solid, stable and capable of carrying the load of the panels to be installed.
- Remove all loose particles, dust and grease.
- A speedier cure can be attained by moistening the substrates if needed.

Application

- Shake the canister vigorously at least 20 times. Remove the protective cap and screw onto the illbruck PU foam gun.
- For internal applications: Starting at the middle of the panel, apply a bead of PU010 adhesive across the full width of the board or panel and repeat every 300 mm.
- For external applications (EIFS): Apply a bead of PU010 Panel Adhesive around the perimeter of the surface to be bonded. Then across the full width of the board or panel at 300 mm intervals.
- For best results always work with the canister in a vertical position and keep the valve pointed downwards.
- Move the panel into place and press firmly to ensure a good contact. Hold in position for 2-3 minutes, heavier panels may require additional support during curing.



PU010

Panel Adhesive



Usage / Purpose

PU010 is a rapid curing gun grade polyurethane adhesive. It is ideal for the rapid installation of plasterboard, insulation or acoustic panels, EIFS, roof decking and similar sheet materials. PU010 is compatible with many common substrates including masonry, concrete, timber and metal.

Key Benefits

- An easy to use alternative to mortars and dry wall adhesives
- Ideal for bonding plasterboard, insulation and EIFS panels
- Expands to fill gaps, cavities and uneven surfaces
- Compatible with a wide range of common building substrates

PU010

Panel Adhesive



Coverage

A single canister of PU010 is sufficient to bond approximately 5 m² of panel.

Cleaning

Remove excess adhesive immediately with AA290 PU Foam Cleaner. Ensure surface is solvent resistant before cleaning. Cured adhesive can only be removed mechanically.

Health & Safety Precautions

Safety data sheet must be read and understood before use.



Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in

accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



Tremco CPG UK Limited
Coupland Road
Hindley Green, Wigan WN2 4HT
United Kingdom
T: +44 1942 251400
F: +44 1942 251410

info.uk@cpg-europe.com
www.cpg-europe.com