



enquiry@indasol.co.uk www.indasol.co.uk

2020-E Two Part Clear Methacrylate Adhesive

Product Description:

Instructions for use:

components.

1. Always consult MSDS before using 2020-E.

3. Remove cap, and attach mixer nozzle.

2. Carry out surface preparation where required.*

4. Dispense sufficient adhesive to ensure equal mix.

adhesive prior to cure using a suitable cleaner *

5. Apply adhesive to one surface and assemble components carefully, clamping if required

6. It is always easier to remove any excess

Allow the adhesive sufficient time to achieve handling strength before moving or unclamping

2020-E is produced in a two component transparent structural methacylate adhesive, designed for the bonding of high strength plastic and composite applications. This grade is an advanced liquid composite, which combines shock resistance and toughness from a unique blend of hybrid rubbers, with a high tensile shear strength from an innovative liquid plastic resin. Due to demand we produce this system in both a medium viscosity and high viscosity non slump version. Once bonded this fusion of chemistries achieves an ultra high strength bond with excellent chemical and environmental resistance.

Typical Applications:

2020-E is very versatile, and can bond a wide variety of substrates to plastic without the need for surface primers or conditioners. Typical examples shown below:

Repairing polycarbonate headlights.
Bonding outdoor lighting lenses and fixtures.
Assembling electric meter housings and covers.

-Bonding polycarbonate letters in the sign industry.

-Bonding acrylic in POS manufacture.

Properties of uncured Material:

Resin	Methacrylate Blend	
Colour	Clear	
Appearance	Transparent Liquid	
Viscosity Spindle 6 @ 20rpm	10,000 cps	
Cure System	Exothermic	
Open Time	1-2 Minutes @20°C	
Handling Strength	4-5 Minutes@ 20°C	

Performance of cured material:

ASTM D1002 Lapshear	Acrylic Plastic 8.2	Nmm2		
ASTM D1002 Lapshear	Polycarbonate 12.5	5 Nmm2		
Gap Fill	3mm			
Temperature Range	-55°C to 125°C			

Packaging, Storage and Shelf Life:

2020-E should be stored unopened in a cool dry location, out of direct sunlight. Stored correctly, this grade can offer a 6 month shelf life from manufacture. 2020-E is available in 25ml, 50ml and 400ml Nylon cartridges for use with a dispensing gun.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. Industrial Adhesive Solutions Limited shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Please contact us for further assistance and information.



For further information, samples and a demonstration, please contact: 0121 556 9900 0121 556 9034 enquiry@indasol.co.uk For our Ireland sales manager please contact us on 07795 151814

www.indasol.co.uk

NEXT DAY DELIVERY AVAILABLE 🚛 🤇