

TECHNICAL DATA SHEET

5997 HD SCRIM TAPE

Indasol HD scrim is available in a variety of thickness and slit widths.

5997 is 700 micron self wound double sided adhesive tape with internal scrim to give additional strength in use.

The adhesive is coated onto a 100gsm kraft siliconised release liner.

TECHNICAL DATA

Thickness	: 700µm	
Release Liner	: Siliconised kraft liner paper 100g/m ²	
Tensile Strength	: 88 N/25mm	
Elongation at break	: 12%	
Peel Strength	: Open side (20 mins)	45 N/25mm
	: (FINAT FTM 1 – Stainless Steel)	1.8 kN/m
	: Open side (24 hrs)	65 N/25mm
	: (FINAT FTM 1 – Stainless Steel)	2.6 kN/m
	: Closed side (20 mins)	60 N/25mm
	: (FINAT FTM 1 – Stainless Steel)	2.4 kN/m
	: Closed side (24 hrs)	65 N/25mm
	: (FINAT FTM 1 – Stainless Steel)	2.6 kN/m
Initial Tack	: (FINAT FTM 9 – Stainless Steel)	18 N/25mm 0.7 kN/m
Shear Strength (3kg static shear)	: >800 hours	
Service Temperature	: 5°C to 60°C	
Shelf Life	: 2 years (+15°C to 25°C or +50°F to 77°F) And 50% relative humidity in dust free environment before use and in original packaging	

Whilst all reasonable care is taken in compiling technical data on the company's products, all recommendations or suggestions regarding the use of such products are made without guarantee, since the conditions of use are beyond the control of the Company. It is the customer's responsibility to satisfy himself that each product is fit for the purpose for which he intends to use it, that the actual conditions of use are suitable and that in the light of continued research and development the information relating to each product has not been superseded.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. Industrial Adhesive Solutions Limited shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Please contact us for further assistance and information.



For further information, samples and a demonstration, please contact:

 0121 556 9900  0121 556 9034  enquiry@indasol.co.uk

For our Ireland sales manager please contact us on 07795 151814

NEXT DAY DELIVERY AVAILABLE 

www.indasol.co.uk