

# Technical Data Sheet

## 9660 PERM PEEL FILMIC – DOUBLE SIDED TAPE AMBER OR WHITE PAPER LINER

| TECHNICAL DETAILS                              | TYPICAL VALUE | UNITS   |
|--|---------------|---------|
| Thickness, adhesive + carrier                  | 0.050         | mm      |
| Release liner thickness                        | 0.075         | mm      |
| 180 degree peel adhesion: Open side            | 400           | N/m     |
| Peelable side                      Closed side | 150           | N/m     |
| Polyester loop tack: Open side                 | 800           | N/m     |
| Closed side                                    | 100           | N/m     |
| Liner release                                  | 10            | N/m     |
| Tensile strength                               | 4600          | N/m     |
| Elongation at break                            | 12            | %       |
| Service temperature                            | -20 to +120   | Deg. C. |
| Recommended application temperature            | +5 to +25     | Deg. C. |
| Shear adhesion, 1Kg @ 23 deg. C.               | >2            | Hours   |
| Shelf life                                     | 12            | Months  |
| Test Methods: BS 7116                          |               |         |

Unless stated otherwise all values given are average. All of the tapes in our range should be thoroughly tested on the substrates in the particular application they are intended for. The customer has to decide on the tapes suitability for the intended application.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. Industrial Adhesive Solutions Limited shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Please contact us for further assistance and information.



For further information, samples and a demonstration, please contact:

 0121 556 9900  0121 556 9034  enquiry@indasol.co.uk

For our Ireland sales manager please contact us on 07795 151814

**NEXT DAY DELIVERY AVAILABLE** 

**www.indasol.co.uk**