

TECHNICAL DATA SHEET



INDASOL 900 & 900 BLACK

Page 1 of 3

DESCRIPTION:

Indasol 900 & 900 Black is a new generation of 2 part 1:1 component mixing structural acrylic adhesives. It is fast setting when mixed via a static mix nozzle at room temperatures.

Indasol 900 & 900 Black demonstrates improved impact strength, peel shear and tensile resistance and exterior performance. Because it is a thixotropic, non-sag adhesive, the mixed material is ideal for all types of gap filling requirements on steel, aluminium, polycarbonates and general plastics. It is also very good for vertical surface bonding without running. Indasol 900 & 900 Black exhibits excellent structural strength even without priming the surfaces. Owing to its macro molecular structure, the bonds formed show excellent durability and high peel strength even when filling large gaps and demonstrate excellent solvent and environmental resistance to moisture, hydro-carbon fuels, lubricants, cleaning chemicals and fluids.

TYPICAL USAGES:

Structural bonding in the sign industry of most Signmaking materials especially mild and stainless steels, aluminium, polycarbonate and acrylic sheets, composite panels and even stone and ceramics where high impact strengths are needed. The thixotropic nature of Indasol 900 & 900 Black is ideal for bonding Bighead fasteners and other locators.

Other applications include wind turbines, vehicle roofs, fibreglass, sports goods, automotive spoilers, vents, housings. The high temperature adhesive formulation allows for bonding metal parts prior to powder-coating and oven stoving cycles.

CURING CYCLE:

Once mixed at the 1:1 ratio the working time of the Indasol 900 & 900 Black is the period whereby the adhesive remains fluid and is easily transferable between two or more mating surfaces.

Temperature, volume and substrate have a direct effect on the length of this period as the adhesive cures by an exothermic reaction. Higher temperatures and larger volumes speed the reaction causing a reduction in open and cure time.

Lower temperatures and smaller volumes slow the reaction time extending both the open time and ultimate full.



NEXT DAY DELIVERY AVAILABLE

For further information, samples and a demonstration, please contact:

0121 556 9900 **technical@indasol.co.uk**

For our Ireland sales manager please contact us on 07795 151814

www.indasol.co.uk

TECHNICAL DATA SHEET

INDASOL 900 & 900 BLACK

Page 2 of 3

APPLICATION INSTRUCTIONS:

- Always consult SDS before using Indasol 900 & 900 Black for the first time.
 - Carry out surface preparation where required.
 - Remove cap and burp cartridge then attach mixer nozzle.
 - Dispense sufficient adhesive to ensure equal mix.
 - Apply adhesive to one surface and assemble components carefully, clamping if required.
 - It is always easier to remove any excess adhesive prior to cure using a suitable cleaner.
- Allow the adhesive sufficient time to achieve handling strength before moving or unclamping.

COMPATIBLE SUBSTRATES:

Aluminium	Wood
Stainless Steel	Granite
Mild Steel	Marble
UPVC	Urethanes
Polyesters	Vinly Esters
ABC	Glav/Zinc coated
Acrylic	Thermoset
FRP	Gelcoa
GRP	Epoxy Laminate

UNCURED PROPERTIES:

Resin	Methyl Methacrylate
Colour	Yellow/White & White/Grey
Appearance	Thixotropic Gel
Viscosity Brookfield T Bar	400,000 to 600,000cps
Cure System c	Exothermic
Open Time	7 minutes @ 20°C 10g mass
Handling Strength	12 minutes @ 20°C 10g mass
SG Part A	0.96
SG Part B	0.91



NEXT DAY DELIVERY AVAILABLE 

For further information, samples and a demonstration, please contact:

 **0121 556 9900**  **technical@indasol.co.uk**

For our Ireland sales manager please contact us on 07795 151814

www.indasol.co.uk

TECHNICAL DATA SHEET



INDASOL 900 & 900 BLACK

Page 3 of 3

CURED PROPERTIES:

ASTM D1002 lapshear	Average over 16 tests
Aluminium	20.4Nmm ²
Stainless Steel	38.4Nmm ²
Mild Steel	38.4Nmm ²
GRP	Substrate failure
ABS	Substrate failure
Acrylic	Substrate failure
ASTM D638 Tensile	Up to 30 Nmm ²
Gap Fill	4mm
Standard Temperature	-55°C to 120°C
Paint Bake Cycle	20 minutes @ 220°C
Aluminium Lapshear following moist cataplastm 7 days @ 70°C	26.7 MPA
Peel Strength Aluminium	6KN/m
Shore hardness	75 shore D

Storage & Shelf life:

Indasol 900 & 900 Black should be stored unopened in a cool dry location, between 6-12°C, out of direct sunlight. Stored correctly, this grade can offer a 12-month shelf life from manufacture.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. Indasol Group shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Please contact us for further assistance and information.



NEXT DAY DELIVERY AVAILABLE

For further information, samples and a demonstration, please contact:

0121 556 9900 **technical@indasol.co.uk**

For our Ireland sales manager please contact us on 07795 151814

www.indasol.co.uk