

# TECHNICAL SAFETY DATA SHEET

## UHB 18064G FOAMED ACRYLIC TAPE

TECHNICAL DESCRIPTION	UNIT OF MEASUREMENT	TECHNICAL VALUE
CARRIER		ACRYLIC FOAM
ADHESIVE		ACRYLIC
COLOUR		GREY
THICKNESS	mm	0.64
DENSITY OF FOAM	kg/m <sup>3</sup>	780
RELEASE LINER		RED PE
180° PEEL ADHESION ASTM D-3330	g/25mm	3500
TENSILE ADHESION (T-BLOCK TEST) ASTM D-897	g/cm <sup>2</sup>	7000
DYNAMIC SHEAR ASTM D-1002	g/cm <sup>2</sup>	≥4000 (after 20 mins) ≥6800 (after 24 hours)
TEMPERATURE RESISTANCE SHORT TERM	°C	160
TEMPERATURE RESISTANCE LONG TERM	°C	100
LOW TEMPERATURE RESISTANCE	°C	-40
U.V. RESISTANCE		GOOD

Unless stated otherwise all values given are average. All of the tapes in our range should be thoroughly tested on the substrates in the particular application they are intended for. Industrial Adhesive Solutions and Avanti Tapes Ltd. will not be responsible for product failure unless full testing has been completed. The customer has to decide on the tapes suitability for the intended application.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. Industrial Adhesive Solutions Limited shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Please contact us for further assistance and information.



For further information, samples and a demonstration, please contact:

 0121 556 9900  0121 556 9034  enquiry@indasol.co.uk

For our Ireland sales manager please contact us on 07795 151814

**NEXT DAY DELIVERY AVAILABLE** 

**www.indasol.co.uk**